

### Bitumen 40/50

Test method	Specification	
D-70	1.01-1.06	Specific gravity @25/25 C
D-5	40/50	Penetration @25 C
D-36	52/60	Softening point C
D-113	100 min	Ductility @25 C
D-6	0.2 max	Loss on heating (wt)%
D-6 & D-5	20 max	Drop in penetration after heating %
D-92	250min	Flash point C
D-4	99.5 min	Solubility in CS2 (wt)%
*A.A.S.H.O.T.102	negative	Spot test

### BITUMEN 60/70

	Specification	Test method
Specific gravity @25/25 C	1.01-1.06	D-70
Penetration @25 C	60/70	D-5
Softening point C	49/56	D-36
Ductility @25 C	100 min	D-113
Loss on heating (wt)%	0.2 max	D-6
Drop in penetration after heating %	20 max	D-6 & D-5
Flash point C	250min	D-92
Solubility in CS2 (wt)%	99.5 min	D-4
Spot test	negative	*A.A.S.H.O.T.102